



## Tech Data Sheet

## SM1201A

### EXTREME LOW TEMPERATURE SILICONE GREASE

#### PRODUCT DESCRIPTION

SM1201A is a lubricating grease designed for demanding applications where maximum surface contact is required under load and where extremely low temperatures are expected. SM1201A features an application operating range of -150o F to 475o F, low volatility, non-corrosive, plus excellent dispersion and stability. SM1201A is useful as a lubricant in extreme high pressure applications including aircraft and marine, mine fuse parts, low temperature parts and high pressure/low speed parts.

Product Data	
Typical Properties	
Appearance	Yellow
Application Temperature	-150° F to 475° F
Unworked Penetration (240 – 300 range)	260
Worked Penetration (270 min)	280
Evaporation	< 1.5% @ 475° F
Specific Gravity	1.00 - 1.06
Hegman Grind	2.5 mils
Typical Electricals	
Dielectric Strength (50 mil)	615 V/mil
Dielectric Constant (1 kHz)	2.9
Dissipation Factor (1 kHz)	0.0025
Volume Resistivity (Ω-cm)	4.1 X10 <sup>14</sup>

#### Features & Benefits

- Hydrolytic Stability
- Water Repellent
- Radiation Resistant
- Chemically Inactive
- Non-corrosive
- Chemical & Thermal Resistant
- Dielectric Strength

**Applications/Use**

- Aircraft / Marine Cable
- Mine Fuse Parts & Electrical Connectors
- Low-temperature moving parts
- High Pressure / Low speed parts

**Safety**

- IN CASE OF EYE CONTACT, flush immediately with plenty of clean water.
- IN CASE OF SKIN CONTACT, wash thoroughly with soap and water.
- IF SWALLOWED, DO NOT induce vomiting. Consult physician or regional poison control center immediately.
- KEEP OUT OF REACH OF CHILDREN.
- Consult MSDS for further information.

**Storage and Shelf Life**

Keep container closed and store at room temperature but not exceeding 100°F. SM1201A has a shelf life of 18 months from the date of manufacture/shipment. Keep away from excessive heat.

**USERS PLEASE READ**

The information and data contained herein is believed to be accurate and reliable; however, it is the user's responsibility to determine suitability of use. Since the supplier cannot know all the uses, or the conditions of use to which these products may be exposed, no warranties concerning the fitness or suitability for a particular use or purpose are made.

It is the user's responsibility to thoroughly test any proposed use of our products and independently conclude satisfactory performance in the application.

Likewise, if the application, product specifications or manner in which our products are used require government approval or clearance, it is the sole responsibility of the user to obtain such authorization.

The supplier warrants only that its products will meet its specifications. There is no warranty of merchantability or fitness for use, nor any other express or implied warranty. The user's exclusive remedy and the supplier's sole liability is limited to refund of the purchase price or replacement of any product shown to be otherwise than as warranted. The supplier will not be liable for incidental or consequential damages of any kind.

Suggestions of uses should not be taken as inducements to infringe on any patent.